

ZEONOR® 1060R

Diagnostic Grade

Cyclo-Olefin Polymer resin with a high flow rate for ease of molding. Compatible with EtO, Gamma irradiation and vaporized hydrogen peroxide sterilization.

Property	Value	Unit	Test Standard
Physical Properties			
Specific gravity	1.01	-	ASTM D792
Melt flow rate (MFR) (230 °C, 21.18 N)	12.6	g/10min	ISO 1133
Water absorption (23 °C/24 hrs)	0.01	%	ASTM D570
Water vapor transmission (40 °C, 90% rh, @100µm thickness)	/	g/m ² ·day	ASTM F1249
Oxygen transmission (23 °C, 0% rh, @100µm thickness)	/	cm ³ /(m ² ·day·atm)	ASTM D3985
Optical Properties			
Light transmittance (3mm thickness)	91.5	%	ASTM D1003
Mechanical Properties			
Tensile strength	52.01	MPa	ISO 527
Tensile modulus	2204	MPa	ISO 527
Flexural modulus	2078	MPa	ISO 178
Flexural strength	82.04	MPa	ISO 178
Elongation at break	99.3	%	ISO 527
Izod impact strength (3.2 mm with notch)	34	J/m	ASTM D256
Thermal Properties			
Glass transition temperature	98.8	°C	JIS K7121
Heat deflection temperature (1.82 MPa)	88	°C	ASTM D648
Coefficient of linear thermal expansion	6E-05	cm/cm °C	ASTM E831
Solvent Compatibility			
Alcohols	Good		
Acids/Bases	Good		

Typical properties. Not to be used for purposes of establishing specification(s).