

ZEONOR® 1430R Diagnostic Grade

Cyclo-Olefin Polymer resin that has lower molecular weight for improved flow during molding. Compatible with EtO, Gamma irradiation, vaporized hydrogen peroxide and steam/autoclave sterilization.

Property	Value	Unit	Test Standard
Physical Properties			
Specific gravity	1.02		ASTM D792
Melt flow rate (MFR) (280 °C, 21.18 N)	30	g/10min	ISO 1133
Water absorption (23 °C/24 hrs)	0.01	%	ASTM D570
Water vapor transmission (40 °C, 90% rh, @100µm thickness)	/	g/m ² ·day	ASTM F1249
Oxygen transmission (23 °C, 0% rh, @100µm thickness)	/	cm ³ /(m ² ·day·atm)	ASTM D3985
Optical Properties			
Light transmittance (3mm thickness)	91.5	%	ASTM D1003
Mechanical Properties			
Tensile strength	63.87	MPa	ISO 527
Tensile modulus	2467	MPa	ISO 527
Flexural modulus	2303	MPa	ISO 178
Flexural strength	101.7	MPa	ISO 178
Elongation at break	61.1	%	ISO 527
Izod impact strength (3.2 mm with notch)	24	J/m	ASTM D256
Thermal Properties			
Glass transition temperature	134.5	°C	JIS K7121
Heat deflection temperature (1.82 MPa)	119	°C	ASTM D648
Coefficient of linear thermal expansion	6E-05	cm/cm °C	ASTM E831
Solvent Compatibility			
Alcohols	Good		
Acids/Bases	Good		

Typical properties. Not to be used for purposes of establishing specification(s).